

1) Algemeen

Het montuur

- Polypropyleen

Monolame

- SEBS



2) Kleuren, referenties en gewicht

| Maten | wit | groen | blauw | rood | geel | Gewicht (kg) |
|-------|--------|--------|--------|--------|--------|--------------|
| 30cm | 100301 | 100318 | 100325 | 100332 | 100349 | 0.225 |

| Diameter steel | | Lengte van de steel | Steriliseerbaar |
|----------------|---------|---------------------|-----------------|
| Steel | 27.5 mm | 20 cm | 134 ° |
| Handvat steel | 25.5 mm | | |

3) Verpakking : Verpakt/6st.

| Artikel | EAN artikel | EAN doos | Afm. doos (cm) | St/rij |
|---------|---------------|----------------|----------------|--------|
| 100301 | 5410616100301 | 15410616100308 | 33X30X14 | 6 |
| 100318 | 5410616100318 | 15410616100315 | 33X30X14 | 6 |
| 100325 | 5410616100325 | 15410616100322 | 33X30X14 | 6 |
| 100332 | 5410616100332 | 15410616100339 | 33X30X14 | 6 |
| 100349 | 5410616100349 | 15410616100346 | 33X30X14 | 6 |

Goederen-code: 96039091

4) Technische specificaties

Geschikt voor de voedingssector

Advies voor gebruik : Het is aanbevolen om onze monolame vloerwissers te steriliseren voor gebruik. Steriliseerbaar tot 134°C.

Onze **MONOLAME** vloerwissers voldoen aan de huidige HACCP normen.

Onze volledige kleurgecodeerde lijn (wit-rood-blauw-groen-geel) helpt de kwaliteitsmanagers om kruisbesmettingen tijdens de productie te voorkomen.

Chemical resistance of general Cawiton® SBS and SEBS grades

| | |
|------------------------|---|
| Acetic acid, 5 % | S |
| Acetone | U |
| Ammonia | S |
| Bleach | L |
| Butter | L |
| Cola beverage | S |
| Detergent, 30 % | S |
| Ethyl acetate | U |
| Ethylalcohol, diluted | S |
| Ethylalcohol, 96 % | L |
| Gasoline | U |
| Hydrochloric acid, 3 N | S |
| Hydrogen peroxide, 6 % | S |
| Mayonaise | L |
| Ketchup | S |
| Hand lotion | S |
| Methylalcohol | L |
| Milk | E |
| Mineral oil | L |
| Nitric acid, 3 N | S |
| Orange juice | S |
| Salad oil | L |
| Sodium hydroxide, 3 N | S |
| Sulfuric acid | S |
| Terpentine | U |
| Toluene | U |
| Water | E |

E = Excellent
S = Satisfactory
L = Limited
U = Unsatisfactory

(Deze informatie kan evolueren in de tijd, en is informatief, zonder contractuele waarde).



Chemical resistance of Cawiton compounds

| | | | | | | | | |
|----|--|---|-----|---------------------------------------|---|-----|---------------------------------|---|
| 1 | Acetaldehyde | R | 73 | Ethyl bromide | R | 145 | Oils vegetable | T |
| 2 | Acetates (low mol wt) | R | 74 | Ethyl chloride | R | 146 | Oleic acid | R |
| 3 | Acetic acid (less than 5%) | R | 75 | Ethylamine | R | 147 | Oxalic acid | R |
| 4 | Acetic acid (more than 5%) | R | 76 | Ethylene chlorohydrin | R | 148 | Oxygen (gas) | R |
| 5 | Acetic anhydride | T | 77 | Ethylene dichloride | R | 149 | Ozone | R |
| 6 | Aceto nitrile | R | 78 | Ethylene glycol | T | 150 | Perchloric acid | R |
| 7 | Acetone | T | 79 | Ethylene oxide | R | 151 | Perchloroethylene | T |
| 8 | Acetyl bromide | R | 80 | Fatty acids | T | 152 | Phenol | N |
| 9 | Acetyl chloride | R | 81 | Ferric chloride | R | 153 | Phosphoric acid (ortho) | R |
| 10 | Air | R | 82 | Ferric sulfate | R | 154 | Phthalic acid | N |
| 11 | Alcohols | T | 83 | Ferrous chloride | R | 155 | Plating solutions | R |
| 12 | Aliphatic hydrocarbons (C4 and higher) | N | 84 | Ferrous sulfate | R | 156 | Polyglycol | T |
| 13 | Aluminium chloride | R | 85 | Fluoborate salts | R | 157 | Potassium carbonate | R |
| 14 | Aluminium sulphate | R | 86 | Fluoboric acid | R | 158 | Potassium chlorate | R |
| 15 | Alums | R | 87 | Fluo-silicic acid | R | 159 | Potassium hydroxide (med.conc.) | R |
| 16 | Ammonia (gas, liquid) | R | 88 | Formaldehyde | R | 160 | Potassium hydroxide (conc.) | R |
| 17 | Ammonium acetate | R | 89 | Formic acid | R | 161 | Potassium iodide | R |
| 18 | Ammonium carbonate | R | 90 | Freon | T | 162 | Propinal Aldehyde | R |
| 19 | Ammonium chloride | R | 91 | Gasoline (non-aromatic) | N | 163 | Pyridine | R |
| 20 | Ammonium hydroxide | R | 92 | Gasoline (high-aromaticity) | N | 164 | Sea water | R |
| 21 | Ammonium nitrate | R | 93 | Glucose (dextrose) | R | 165 | Silicone fluids | R |
| 22 | Ammonium phosphate | R | 94 | Glue (water base) | R | 166 | Silicone oil | R |
| 23 | Ammonium sulfate | R | 95 | Glycerine | T | 167 | Silver nitrate | R |
| 24 | Amyl acetate | N | 96 | Grease | T | 168 | Skydrol | N |
| 25 | Amyl alcohol | N | 97 | Hydriodic acid | R | 169 | Soap solutions | R |
| 26 | Amyl chloride | N | 98 | Hydro bromic acid | R | 170 | Sodium bicarbonate | R |
| 27 | Aniline | T | 99 | Hydrochloric acid | R | 171 | Sodium bisulfate | R |
| 28 | Aniline hydrochloride | T | 100 | Hydrochloric acid (med.conc.) | R | 172 | Sodium bisulfite | R |
| 29 | Antimony salts | R | 101 | Hydrochloric acid (conc.) | R | 173 | Sodium borate | R |
| 30 | Aqua regia (75% HC1 25% HNO ³) | R | 102 | Hydrocyanic acid | R | 174 | Sodium carbonate | R |
| 31 | Aromatic hydrocarbons | N | 103 | Hydrofluoric acid | R | 175 | Sodium chlorate | R |
| 32 | Arsenic salts | R | 104 | Hydrogen peroxide (dil.) | R | 176 | Sodium chloride | R |
| 33 | Barium salts | R | 105 | Hydrogen peroxide (conc.) | R | 177 | Sodium terocyanide | R |
| 34 | Benzaldehyde | N | 106 | Hydrogen sulfide | T | 178 | Sodium hydrosulfite | R |
| 35 | Benzene | N | 107 | Hypochlorous acid | R | 179 | Sodium hydroxide (dil.) | R |
| 36 | Benzene sulfonic acid | R | 108 | Iodine and solutions | T | 180 | Sodium hydroxide (med.conc.) | R |
| 37 | Benzoic acid | N | 109 | Iron salts | R | 181 | Sodium hydroxide (conc.) | R |
| 38 | Benzyl alcohol | N | 110 | Isopropanol (IPA) | R | 182 | Sodium hypochlorite (below 5%) | R |
| 39 | Bleaching liquors (non aromatic) | R | 111 | Kerosene | N | 183 | Sodium hypochlorite (above 5%) | R |
| 40 | Boric acid | R | 112 | Ketones (water soluble) | R | 184 | Sodium nitrate | R |
| 41 | Bromine | R | 113 | Lactic acids | R | 185 | Sodium silicate | R |
| 42 | Break fluid | R | 114 | Laquer solvents | N | 186 | Sodium sulfide | R |
| 43 | Butane | N | 115 | Lactic acids | R | 187 | Sodium sulfite | R |
| 44 | Butyl acetate | N | 116 | Lead Acetate | R | 188 | Steam (up to 40 psi) | T |
| 45 | Buryl alcohol (Butanol) | T | 117 | Linseed Oil | N | 189 | Stearic acid | R |
| 46 | Butyric acid | R | 118 | Lithium hydroxide | R | 190 | Styrene | N |
| 47 | Calcium oxide (diluted) | R | 119 | Magnesium chloride | R | 191 | Sulfur chloride | R |
| 48 | Calcium salts | R | 120 | Magnesium sulfate | R | 192 | Sulfur dioxide | R |
| 49 | Carbon (di)sulfide | N | 121 | Malic acid | R | 193 | Sulfuric hezafluoride | R |
| 50 | Carbon dioxide | R | 122 | Manganese salts | R | 194 | Sulfuric trioxide | R |
| 51 | Carbon tetrachloride | T | 123 | Mercury salts | R | 195 | Sulfuric acid (dil.) | R |
| 52 | Chloracetic acid | R | 124 | Methane | N | 196 | Sulfuric acid (med.conc.) | R |
| 53 | Chlorine (wet) | R | 125 | Methanol (<40%) | R | 197 | Sulfuric acid (conc.) | R |
| 54 | Chlorine (dry) | R | 126 | Methanol (>40%) | T | 198 | Sulfurous acid | R |
| 55 | Chlorobenzene | N | 127 | Methyl chloride | R | 199 | Swimming pool water | R |
| 56 | Chlorobromomethane | N | 128 | Methyl-ethyl-ketone (MEK) | R | 200 | Tannic acid | R |
| 57 | Chloroform | N | 129 | Methylen chloride | R | 201 | Tanning extracts | R |
| 58 | Chlorosulfonic acid | R | 130 | Milk | R | 202 | Tartaric acid | R |
| 59 | Chromic acid | R | 131 | Mixes acid (40% sulphuric 15% nitric) | R | 203 | Tin salts | R |
| 60 | Chromium salts | R | 132 | Molybdenum disulfide | R | 204 | Titanium salts | R |
| 61 | Citric Acid | R | 133 | Monoethanolamine | T | 205 | Toluene (toluol) | N |
| 62 | coolant | R | 134 | Naphtha | N | 206 | Trichloroacetic acid | R |
| 63 | Copper salts | R | 135 | Natural gas | N | 207 | Trichloroethylene | N |
| 64 | Cresol | N | 136 | Nickel salts | R | 208 | Tri-sodium | R |
| 65 | Cyclohexane | N | 137 | Nitric acid (diluted) | R | 209 | Turpentine | N |
| 66 | Cyclohexanone | N | 138 | Nitric acid (med. Conc.) | R | 210 | Urea | R |
| 67 | Diacetone alcohol | R | 139 | Nitric acid (conc.) | R | 211 | Uric Acid | R |
| 68 | Dimethyl formamide | R | 140 | Nitrobenzene | N | 212 | Vinyl plastisol | N |
| 69 | Essential oils | R | 141 | Nitrogen oxides | R | 213 | Water | R |
| 70 | Ethers | N | 142 | Nitrous acid | R | 214 | Water (brine) | R |
| 71 | Ethyl acetate | R | 143 | Oils animal | T | 215 | Xylene (Xyol) | N |
| 72 | Ethyl alcohol (Ethanol) | T | 144 | Oils mineral | T | 216 | Zinc chloride | R |

R: resistant

N: not resistant

T: testing recommended before use

